

# **2K CLEAR**

#### Description

- 2K Acrylic Urethane Clear Coat
- Medium Solids
- Cost effective
- 5L 26-22210955

#### **Technical Summary**

- High gloss
- Excellent through cure
- Excellent leveling and flow





# **2K CLEAR**

Working process		
	Substrates:	• Basecoat
	Pretreatment / Cleaning:	Clean with Duxone <sup>®</sup> Wax and Grease Remover
	Application:	Use recommended respirators. Refer to relevant Material Safety Data Sheet (MSDS)
		2:1 with Duxone <sup>®</sup> 2K Hardener medium or Duxone <sup>®</sup> 2K Hardener slow
		Up to 10% Duxone <sup>®</sup> 2K Thinner
<b>∏</b> s		16 – 21s Ford Cup 4 / 20°C 16 – 20s DIN 4/ 20°C
		1.3 - 1.4 mm 400 - 500 kPa 2 coats = 50 - 60 $\mu$ m
		1.5 - 1.7  mm 400 - 500  kPa $2 \text{ coats} = 50 - 60 \mu\text{m}$
$\frac{1}{2}$		<ul> <li>5 - 10 min / 20°C between coats</li> <li>5 - 10 min / 20°C before force drying</li> </ul>
		Air dry: 4 – 5 hours (optimum overnight) / 20°C Bake: 20 minutes / 60°C metal temp.
		10 – 15 min, short wave 15 – 20 min, medium wave



An Axalta Coating Systems Brand DX2K-02-06/14 Aus p.3 of 4

V02





# **2K CLEAR**

### **TECHNICAL DATA**

Flashpoint:	Above +23°C		
Raw Material:	Acrylic Urethane high gloss resin		
Specific Gravity:	0.968 g/mL		
VOC:	535 g/L		
Approx.	$7.7 \text{ m}^2/\text{L}$ at 50 microns DFT		
Coverage:			
Potlife:	2 hours / 20°C		
Cleaning of	Clean after use with Duxone <sup>®</sup> Gun Wash Solvent		
Equipment:			
Important	• For professional use only		
Remarks:	• For small spot repairs and similar applications, Duxone 2K		
	Hardener fast may be used		
This data relates only to the material designated herein and does not apply to use in			
combination with any other material or any process. The data is not to be considered as a			
warranty or quality specification and we assume no liability in connection with its use.			

