

421R 27.08.2014

**VARISPEED** 

### DESCRIPTION

Solvent mixture developed for faster drying and hardening of 2K topcoats or 2K clearcoats. Composition based on catalyst containing special blend of organic solvents.

### **PRODUCTS**

421R Varispeed

### **PROPERTIES**

- Accelerator for small repairs and interior painting with 2K topcoats or 2K clears to provide faster air and forced drying.
- Can be used in: Centari® 500, Centari® 500 HB, Imron® 700, and 3050S.

### **APPLICATION - REMARKS**

### Centari® 500 and Centari® 500 HB

- 421R can be used with the standard thinner and activator to give optimum balance in drying. Maximum amount of 421R is 100 % replacement of the thinner in ready-for-use.

### Imron<sup>®</sup> 700

421R can replace AU370 with maximum 50 %.

#### 3050S

- Maximum amount of 421R is 10 % in volume ready-for-use.
- Do not use 421R together with 256S or XK203.
- Close container after use. This prevents the solvents to evaporate and to lose strength.



421R 27.08.2014

**VARISPEED** 

## PRODUCT PREPARATION

- Product preparation according to the recommendations in the TDS of the selected quality.
- Mix 421R after activation.

## PRODUCT PREPARATION

| Centari® 500  |               |             |               |
|---------------|---------------|-------------|---------------|
|               |               | 20°C        | 20 min x 60°C |
|               | Dust-free     | 40 min      | imm.          |
| (- \sqrt-)    | Dry to handle | 3 hr 30 min | 20 min        |
|               | Tape-free     | 6 hr        | 30 min        |
|               |               |             |               |
| Pot life 20°C | 4 hr          |             |               |

| Centari® 500 HB |               |        |               |
|-----------------|---------------|--------|---------------|
|                 |               | 20°C   | 20 min x 60°C |
|                 | Dust-free     | 50 min | imm.          |
| (- \sqrt-)      | Dry to handle | 5 hr   | 20 min        |
|                 | Tape-free     | 6 hr   | 30 min        |
| Pot life 20°C   | 1 hr 30 min   |        |               |

| Imron <sup>®</sup> 700 |               |        |               |
|------------------------|---------------|--------|---------------|
|                        |               | 20°C   | 20 min x 60°C |
|                        | Dust-free     | 30 min | imm.          |
| (- \sqrt-)             | Dry to handle | 4 hr   | 20 min        |
|                        | Tape-free     | 12 hr  | 1 hr          |
|                        |               |        |               |
| Pot life 20°C          | 3 hr          |        |               |



421R 27.08.2014

**VARISPEED** 

## PRODUCT PREPARATION (CON'D)

| <b>3050S</b> (with Al- | (260)         |        |               |
|------------------------|---------------|--------|---------------|
|                        |               | 20°C   | 20 min x 60°C |
|                        | Dust-free     | 20 min | imm.          |
| (- \sqrt-)             | Dry to handle | 3 hr   | imm.          |
|                        | Tape-free     | 6 hr   | 30 min        |
|                        |               |        |               |
| Pot life 20°C          | 2 hr          |        |               |

| <b>3050S</b> (with XI | (205)         |      |               |
|-----------------------|---------------|------|---------------|
|                       |               | 20°C | 20 min x 60°C |
|                       | Dust-free     | 1 hr | imm.          |
| (- \sqrt-)            | Dry to handle | 3 hr | imm.          |
|                       | Tape-free     | 6 hr | 30 min        |
|                       |               |      |               |
| Pot life 20°C         | 2 hr          |      |               |

#### SAFETY

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.



421R 27.08.2014

**VARISPEED** 

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

All other products referred to in the paint system build-up are from Cromax<sup>®</sup>. System properties will not be valid when the related material is used in combination with any other materials or additives not belonging to Cromax<sup>®</sup>, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.