


Always use correct Personal Protective Equipment


# AD 99 DRIER MIX

## Description



AD 99 Drier Mix is a general blend of metal octoate driers suitable for alkyd resin based paints. AD 99 is used as a drier mix for Spraying Enamel non drying, all colours available. It can also be used for any alkyd paint without driers incorporated.

## Products



### Product Type:

**Colour:** A dark violet liquid

**Pot Life:**

**Induction Time:**

**Density:** 0.950 kg/L

**Recommended DFT:**

**Theoretical Coverage:**

## Properties



**VOC:**

**Volume Solids:** 26.76%


**Boiling Point :** 150%

**Recoat-ability:**

**Dry Time @ 20°C:**

## Directions

### For Use



**Mixing Ratio:** Add 144 g of AD 99 Drier Mix to 4 litres of Spraying Enamel non-drying. Mix in well.


**Thinning:** 20 to 40% with Spraying Thinner or Winter Thinner.

## Health & Safety



For detailed information refer to Safety Data Sheets (SDS). Avoid breathing vapour. Wear protective mask and gloves. Ensure adequate ventilation. If eyes become contaminated flush with water for 15 minutes.

## Transport & Storage



**Sizes:** 1L, 4L

**Dangerous Goods:** 3Y, 3B

**UN:** 1263

**Hazchem:** 3Y

**Packing Group:** III

**Shipment name:** PAINT Related Material (flammable)

**Flash point:** 32°C

No warranty either expressed or implied is made by RALI in this document, which is a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product or its properties shall conform to that description, nor is the description of the product and its properties a warranty by RALI that the goods are suitable for a particular purpose. Do not apply paint if relative humidity is above 85% or temperature is within 3 deg C of Dew Point being the MPT or Minimum Paint Temperature.