



Effective October 5, 2011

Cromax[®] Pro Basecoat

WATERBORNE BASECOAT

Description

1-component, polyurethane based, waterborne basecoat for use in clear over base systems for solid, metallic and pearl colours. Suitable for use on cars, trucks and buses. Composition based on polyurethane copolymer and acrylic latex.

Products

WB01-WB99	Cromax [®] Pro Mixing Color (solid)
WB1001-WB1099	Cromax [®] Pro Mixing Color (effect)
WB2010	Cromax [®] Pro Basecoat Binder I
WB2020	Cromax [®] Pro Basecoat Binder II
WB2030	Cromax [®] Pro Basecoat Viscosity Balancer
WB2040	Cromax [®] Pro Basecoat Controller - Standard Condition
WB2043	Cromax [®] Pro Basecoat Controller - Low Humidity
WB2045	Cromax [®] Pro Basecoat Controller - Low Humidity
WB2091	Cromax [®] Pro Basecoat Blender
WB2075	Cromax [®] Pro Basecoat Activator
TN800W	Cromax [®] Pro Waterborne Reducer

Properties

- Provides ease of application and accurate colour matching.
- The excellent hiding, coverage balance gives significant savings in application time and consumption.
- Can be used for spot, panel and overall repair.
- Controller concept makes Cromax[®] Pro Basecoat flexible in use.
- VOC compliant, conform with directive 2004/42/EC.

Substrates

- All OEM and cured repair finishes, DuPont Refinish 2K primer surfacers or DuPont Refinish 2K surfacers.













Effective October 5, 2011

Cromax[®] Pro Basecoat

WATERBORNE BASECOAT

PRODUCT PREPARATION

	DuPont Refinish colour tools	See colour formula.				
	Mixing ratio	> 30°C		< 30°C		
		Relative Humidity	Controller	TN800W	Controller	TN800W
		< 15%	WB2045	10%	WB2045	-
		15% – 25%	WB2045	10%	WB2043	-
		26% – 35%	WB2043/5	10%	WB2043	-
		36% – 60%	WB2043/0	-	WB2040	-
		> 60% RH	WB2040	-	WB2040	-
		Cromax [®] Pro Basecoat (activated/non activated) Controller (*)	Effect colours (Volume)		Solid colours (Volume)	
	100		100			
	20		10			
Cromax [®] Pro Basecoat WB2075 Controller (*)	Tri-coats/Multi-toning (Volume)		Under the hood colours (Volume)			
	95		90			
	5		10			
	See above mentioned mixing ratios.					
	VOC	100-420 g/l				
	Pot life at 20°C	Non activated:				
		For optimum application properties, use Cromax [®] Pro Basecoat immediately after addition of a Cromax [®] Pro Basecoat Controller. Ideally Cromax [®] Pro Basecoat colours are stored without controller.				
		Activated:				
		Tri-coats/Multi-toning		Under the hood colours		
	Effect Colours	45'		30'		
	Solid Colours	90'		45'		
	Spray viscosity at 20°C	Not applicable.				
	Spray equipment	Conventional guns	Fluid tip	Distance	Pressure	
		Gravity feed	1.2-1.4 mm	15-20 cm	3-4 bar	
		Suction feed	1.4-1.6 mm	15-20 cm	3-4 bar	
		Pressure feed	1.0-1.2 mm	15-20 cm	3-4 bar	
Compliant guns (HVLPH/TE)				According to supplier's specifications		
Gravity feed	1.2-1.3 mm	10-15 cm				
Suction feed	1.4-1.5 mm	10-15 cm				
Pressure feed	0.8-1.1 mm	10-15 cm				
	Number of coats	Effect colours	1.5			
		Solid colours	2			
	Flash time	No flash between coats. Flash till flat before clearcoating. When activated (WB2075) flash 5 - 10 min before bake.				
	DFT	Effect colours	10-20 µ			
		Solid colours	12-25 µ			
	Drying when activated	Bake at 60°C Venturies Air Dry at 21°C	WB2075			
				5%	10%	
				10 - 15 min	15 - 20 min	
				n.a.	n.a.	
		Till flat	O.N.			

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

(*) Homogenize the Cromax[®] Pro Basecoat Controller prior to use by lightly handshaking the can.



Effective October 5, 2011

Cromax[®] Pro Basecoat

WATERBORNE BASECOAT

RECOMMENDED USE

Surface preparation

1. Clean surface with water and soap. Rinse and dry.
2. Degrease with a correct DuPont Refinish preparatory cleaner. Wipe dry with a clean cloth.
3. Repair according to damage.
4. Sand surface:
 - a. mechanical P400 - P500;
 - b. wet P1000 - P1200.
5. Remove all traces of sanding dust, blowing oil-free compressed air.
6. Degrease with a correct DuPont Refinish final cleaner/degreaser. Wipe dry with a clean cloth.
7. Tack rag.

Basecoat application

- Standard: Apply one "closed" coat of Cromax[®] Pro Basecoat with 70 % overlap, followed by a control coat increasing gun distance to the panel.
- Poor hidiers: Apply two "closed" coats of Cromax[®] Pro Basecoat with 70 % overlap, followed by a control coat increasing gun distance to the panel.

Clearcoat application

Only use DuPont Refinish clears 3550S, 3750S, 3760S, 3800S, CC6400 or CC6600. When the basecoat is completely flat, apply a clearcoat. Maximum time before clearcoating is 3 days.

Equipment cleaning

Use demineralised water in a separate specific gun cleaner.

Waste treatment

- The polluted waste water can be either handled as chemical waste or it can be treated with 16.30 that will separate solid from liquid components and reduce your chemical waste by 60 % or more.
- Procedure
Add 1 to 1.5 % of 16.30 to the polluted waste water and mix thoroughly (with mixer) for 3-5 min until you see the solid material separating. Filter out the solid chemical waste. The separated solid waste and water have to be treated according to local regulations.



Effective October 5, 2011

Cromax[®] Pro Basecoat

WATERBORNE BASECOAT

RECOMMENDED USE (con'd)

Remarks

- The addition of a Cromax[®] Pro Basecoat Controller prior to application of Cromax[®] Pro Basecoat is mandatory
- The use of Cromax[®] Pro Basecoat will depend on external conditions (relative humidity, air flow, temperature, ...).
- Under conditions of low humidity, see mixing ratio tabel
- Cromax[®] Pro Mixing Colors have to be thoroughly stirred before weigh-out and the Cromax[®] Pro Basecoat colour has to be mixed immediately after weigh-out.
- Spray gun must be stainless steel.
- Mix Cromax[®] Pro Basecoat in a plastic can with a plastic stirring rod or the dedicated mixing rod.
- For mixing rod information, see specific TDS.
- Material has to be stored at a temperature between 15°C and 35°C.
- Material has to be at room temperature before use.
- TN800W can only be used in conditions > 30°C.

Product data

Theoretical coverage: 11-16.5 m²/l at recommended DFT - ready-to-spray
Directive 2004/42/EC: 2004/42/IIB(d)(420)420: The EU limit value for this product (product category: IIB(d)) in ready to use form is maximum 420 g/l of VOC. The VOC content of this product in ready to use form is maximum 420 g/l.

Safety

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.



Effective October 5, 2011

Cromax[®] Pro Basecoat

WATERBORNE BASECOAT

REPAIR SYSTEMS


Spot repair

1. Clean surface with water and soap. Rinse and dry.
2. Degrease with a correct DuPont Refinish preparatory cleaner. Wipe dry with a clean cloth.
3. Repair with recommended undercoats.
4. Sand treated spots as recommended, finish with P500 orbital or P1000 wet manual.
5. Prepare complete fade-out area with a non silicone containing rubbing compound or sand wet with P1200.
6. Rinse with water and dry.
7. Degrease with a correct DuPont Refinish final cleaner/degreaser. Wipe dry with a clean cloth.
8. Tack rag.
9. Use the following application method.

(1) Apply WB2091 in the fade-out area.

(2) Apply 1.5 coats of basecoat, extending 2nd coat beyond the previous one, into the wet blender.

(3) Apply the clearcoat on the entire panel after the last coat of the basecoat is completely flat.



Copyright © 2011 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.