

P7W/P7/P7B

27.08.2014

PRIMEPOX

DESCRIPTION

2-component chromate-free epoxy primer-surfacer.

Colour: white, off white, black

Composition based on epoxy/polyamide resin.

PRODUCTS

P7W	Primepox – white
P7	Primepox – off white
P7B	Primepox - black
P72	Epoxy Activator
THP710	Thinner Standard
THP711	Thinner Slow

PROPERTIES

- Very good corrosion and chemical resistance.
- Excellent adhesion on properly treated metal substrates.
- Recommended as a 1st coat over new metal constructions e.g. buses, trucks and vehicles.
- Very good filling properties. Suitable for use over rough substrates e.g. gritblasted metals.
- Compliant with RVI specifications.
- High humidity resistance and good flexibility.
- Shop primer.
- Part of ValueShade® concept.
- P7 can be tinted with PT PowerTints® (up to max.10 % by weight).
- Can be coated with all Imron® Fleet Line 2K surfacers or Imron® Fleet Line topcoats.
- VOC compliant, conform with directive 2004/42/EC.

SUBSTRATES








- Bare metals: steel, aluminium and galvanised steel.
- OEM finishes.
- Cured repair finishes.
- Polyester putties.

P7W/P7/P7B

27.08.2014

PRIMEPOX

PRODUCT PREPARATION

	Mixing ratio ValueShade®		P7W	P7B	P7	P7B
	ValueShade® 1		100	0	-	-
	ValueShade® 2		95	5	100	0
	ValueShade® 3		85	15	90	10
	ValueShade® 4		60	40	60	40
	ValueShade® 5		25	75	30	70
	ValueShade® 6		5	95	10	90
	ValueShade® 7		0	100	0	100
Mixing ratio		Standard		Large surface/High temp.		
			Volume	Weight	Volume	Weight
		P7W/P7/P7B	5	100	5	100
		P72	1	11	1	11
		THP710	1-2	10-20	-	-
THP711	-	-	1-2	10-20		
VOC	504-540 g/l					
Pot life at 20°C	8 hr					
	Spray viscosity at 20°C	DIN 4 FORD 4	5:1:1	5:1:1.5	5:1:2	
			27-33 s	22-24 s	18-20 s	
			31-38 s	24-26 s	20-22 s	
	Spray equipment	Compliant guns	Fluid tip	Distance	Pressure	
			Gravity feed	1.4-1.6 mm	15 cm	According to supplier's specifications
			Suction feed	1.5-1.7 mm	15 cm	
			Pressure feed	1.1-1.4 mm	15 cm	
			Conventional guns	Gravity feed	1.5-1.7 mm	20-25 cm
Suction feed	1.6-1.8 mm	20-25 cm		3-4 bar		
Pressure feed	1.1-1.4 mm	20-25 cm		3-4 bar		
	Number of coats	1-2				
	Flash time	Between coats till flat.				
		Before recoating:	minimum	maximum		
	2K surfacers	30 min	3 days			
	topcoats	1 hr	3 days			
	DFT	25-30 µm/coat				
	Dry to sand at 20°C at 40°C at 60°C	5 hr				
		1 hr				
		45 min				
	IR drying*	Distance	80 cm	* Guideline for short/medium wave IR equipment.		
		Half power	5 min			
		Full power	15-20 min			
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.						

P7W/P7/P7B

27.08.2014

PRIMEPOX

SURFACE PREPARATION

Bare metals (steel, galvanised steel, aluminium or surface treated aluminium)

1. Clean surface with a preparatory cleaner for bare metals. Wipe dry with a clean cloth.
2. Sand and eliminate all rust and corrosion.
3. Remove all traces of sanding dust by blowing with oil-free compressed air.
4. Degrease with a correct final cleaner/degreaser. Wipe dry with a clean cloth.

OEM and cured repair finishes

1. Clean surface with water and soap. Rinse and dry.
2. Degrease with a correct preparatory cleaner. Wipe dry with a clean cloth.
3. Sand surface:
 - a. mechanical with P280 - P320;
 - b. wet with P600.
4. Remove all traces of sanding dust, by blowing with oil-free compressed air.
5. Degrease with a correct final cleaner/degreaser. Wipe dry with a clean cloth.

EQUIPMENT CLEANING

Use a correct solventborne gunwash.

P7W/P7/P7B

27.08.2014

PRIMEPOX

REMARKS

- For optimum surface preparation gritblast to Sa 2 ½.
- Activated material should not be returned to original can of non-activated material.
- P7W/P7/P7B can be applied by brush if no reducer is added to the activated material.
- Material has to be stirred well before use.
- Close can of activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- A limited number of ValueShades® can also be achieved by mixing P7 with PT105:
ValueShade® 3 (VS3) can be obtained by adding 1.5 g of PT105 to 100 g of P7.
ValueShade® 4 (VS4) can be obtained by adding 6.5 g of PT105 to 100 g of P7.
ValueShade® 5 (VS5) can be obtained by adding 10 g of PT105 to 100 g of P7.
- For mixing rod information, see specific TDS.
- Material has to be at room temperature (18-25°C) before use.

PRODUCT DATA

Package viscosity:	3500-5500 mPas
	White 5:1:1 8,3 m ² /l at 50 µ DFT - ready to spray
	White 5:1:2 7,2 m ² /l at 50 µ DFT - ready to spray
Theoretical coverage:	Off white 5:1:1 8,2 m ² /l at 50 µ DFT - ready to spray
	Off white 5:1:2 7,2 m ² /l at 50 µ DFT - ready to spray
	Black 5:1:1 8,2 m ² /l at 50 µ DFT - ready to spray
	Black 5:1:2 7,2 m ² /l at 50 µ DFT - ready to spray
Directive 2004/42/EC:	2004/42/IIB(c) (540)540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

SAFETY

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

P7W/P7/P7B

27.08.2014

PRIMEPOX

All other products referred to in the paint system build-up are from Cromax®. System properties will not be valid when the related material is used in combination with any other materials or additives not belonging to Cromax®, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.