



Standex

VOC-System-Füller U7540

VOC System Filler U7540

- **VOC compliant**
- **Good vertical stability**
- **Good filling properties**
- **Easy to sand**
- **Excellent tension**
- **Good isolating properties**



Technical Description:

- Mix 7:1 with all
Standex VOC Hardeners
- or
- Mix 4:1 with all
Standex HS Hardeners
- Force drying possible
- Air dry overnight / 18-22°C

Stadox VOC System Filler U7540

Substrate:

- Through-hardened sanded paintwork, except TPA
- OEM Primer or EDP, sanded
- Stadox PE Products, sanded
- UP-GF, sanded

Bare metal substrates must be pre-primed with Stadox Acid Primer.

Pretreatment / Cleaning:




For substrate preparation information see Stadox Painting System S1.



Use air fed respirator. Refer to relevant Health and Safety Data Sheets.

**Flash off 5-15 min / 18-22°C
before oven- or infrared drying**

Application: VOC System



7:1 with all
Stadox VOC Hardeners
Potlife 90-120 min / 18-22°C



10% Stadox VOC Thinner
22-24 s / DIN 4mm / 20°C
61-68 s / ISO 4 mm / 20°C



Compliant 1.6 - 1.8 mm
1.5 - 3.0 bar inlet pressure
2 - 3 = max. 250 micron



HVLP 1.6 - 1.9 mm
0.7 bar atomization pressure
2 - 3 = max. 250 micron




Air dry overnight / 18-22°C or
30-40 min. / 60-65°C panel temperature



Short wave 10 - 15 min
(see Stadox Painting System S10)



P800



P400 - P500
Orbital sander



Standocryl VOC Topcoat or Stadox /
Standohyd / Standoblue Basecoat with
Standocryl 2K / VOC Clears

Stadox VOC System Filler U7540

Substrate:

- Through-hardened sanded paintwork, except TPA
- OEM Primer or EDP, sanded
- Stadox PE Products, sanded
- UP-GF, sanded

Bare metal substrates must be pre-primed with Stadox Acid Primer.

Pretreatment / Cleaning:




For substrate preparation information see Stadox Painting System S1.



Use air fed respirator. Refer to relevant Health and Safety Data Sheets.

**Flash off 5-15 min / 18-22°C
before oven- or infrared drying**

Application: HS System



4:1 with all
Stadox HS Hardeners
Potlife 60-90 min / 18-22°C



If necessary 5-10% Stadox 2K Thinner
24-26 s / DIN 4mm / 20°C
68-76 s / ISO 4 mm / 20°C



Compliant 1.6 - 1.8 mm
1.5 - 3.0 bar inlet pressure
2 - 3 = max. 250 micron



HVLP 1.6 - 1.9 mm
0.7 bar atomization pressure
2 - 3 = max. 250 micron




Air dry overnight / 18-22°C or
30-40 min. / 60-65°C panel temperature



Short wave 10 - 15 min
(see Stadox Painting System S10)



P800



P400 - P500
Orbital sander



Standocryl VOC Topcoat or Stadox /
Standohyd / Standoblue Basecoat with
Standocryl 2K / VOC Clears

Stadox VOC System Filler U7540

Flash point:

- 24 - 25 °C / 75.2 - 77.0 °F

Specific Gravity:

- 1.46 - 1.49 g/cm³

Solid Content

(without thinner added):

- 67.3 - 69.0 Weight %
- 45.5 - 47.1 Volume %

VOC (2004/42/EC):

2004/42/IIB(c)(540)540

The EU limit value for this product (productcategory IIB.c) in ready to use form is max 540 g/l VOC. The VOC content of this product in ready for use form is max. 540 g/l.

Theoretical

Coverage:

- 5.6 - 5.8 m²/l at 80 micron dry film thickness

Cleaning of equipment:

Clean after use with Stadox Cleaning Thinner.

Important remarks:

- For better control of the sanding process, spray the filler and allow to flash off. Spray a thin coat of Control Black as a guide coat.
- The filler can be mixed with max. 15% Standocryl VOC Topcoat. Drying and sanding properties will change.
- For film thicknesses of more than 150 micron air dry overnight / 18-22°C or 40 min / 60-65°C panel temperature.

2K Paints react with moisture. Therefore all equipment must be kept moisture free. Ready to use paint materials containing isocyanates can cause irritation of the mucous membranes - and of the respiratory organs, in particular - and cause hypersensitive reactions. There is a risk of hypersensitization if the vapour or spray mist is inhaled. When using materials containing isocyanates, all precautions relating to the handling of solvents should be carefully followed. In particular, care should be taken not to inhale spray mist or vapour. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

For professional use only. The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.