




Standocryl

VOC-Autolack

VOC Topcoat

- **High-quality VOC compliant Topcoat**
- **Economical application**
- **Excellent vertical stability**
- **Very short drying times**
- **Excellent polishability**
- **One visit application**



Technical Description:

- 3:1 VOC System
- Spot Repair / temperatures of 15-20°C
Standox Hardener VOC 10-20
Drying 15-20 min / 60-65°C
- Partial respray / temperatures of 20-25°C
Standox Hardener VOC 20-25
Drying 20-25 min / 60-65°C
- Partial respray / temperatures of 25-30°C
Standox Hardener VOC 25-30
Drying 20-25 min / 60-65°C
- Total respray / temperatures of 30-35°C
Standox Hardener VOC 30-40
Drying 25-30 min / 60-65°C

Standocryl VOC Topcoat

Substrate:

- Stadox Fillers
- Stadox 1K Primer Filler
- Standoflex Primer Filler
- Through-hardened sanded paintwork

Isolate sensitive substrates with Stadox Filler, preferably Stadox VOC Nonstop Primer Filler U7550.

Pretreatment / Cleaning:




For substrate preparation information see Stadox Painting System S1.



Use air fed respirator. Refer to relevant Health and Safety Data sheets.

Alternatively 15% Stadox 2K Thinner can be added.


Application:




3:1 with all
Stadox VOC Hardeners
Potlife 1-1.5 h / 18-22°C




15% Stadox VOC Thinner
18-20 s / DIN 4 mm / 20°C
45-53 s / ISO 4 mm / 20°C



Compliant 1.3 - 1.4 mm
2.0 - 2.5 bar inlet pressure
0.5 + 1 = 50 - 60 micron



HVLP 1.3 - 1.4 mm
0.7 bar atomization pressure
0.5 + 1 = 50 - 60 micron



5-10 min / 18-22°C
final flash-off



Air dry overnight / 18-22°C or
15-30 min. / 60-65°C panel temperature



Short wave
5 min / 50% performance
afterwards 10 min / 100% performance

Standocryl VOC Topcoat

Flash point:

- 23 - 26.4 °C / 73.4 - 79.5 °F

Specific Gravity:

- 0.98 - 1.35 g/cm³

Solid Content

(without thinner added):

- 57.6 - 72.9 Weight %
- 50.3 - 59.0 Volume %

VOC (2004/42/EC):

2004/42/IIB(d)(420)420

The EU limit value for this product (product category: IIB.d) in ready for use form is max 420 g/litre of VOC. The VOC content of this product in ready for use form is max. 420 g/l.

Theoretical

Coverage:

- 10.2-10.6 m²/l at 50 micron dry film thickness

Cleaning of equipment:

Clean after use with Standox Cleaning Thinner.

Important remarks:

- Standocryl VOC Topcoat can be used with:
15% Standox Plasticiser - mix 3:1 with Standox VOC Hardener and 15% Standox VOC Thinner, alternatively Standox 2K Thinner. For soft plastics 30% Standox Plasticiser have to be added.
- Standocryl VOC Topcoat can be overcoated within 24 h without intermediate sanding.
- Allow additional time for heating-up of combi spray booths.

2K Paints react with moisture. Therefore all equipment must be kept moisture free. Ready to use paint materials containing isocyanates can cause irritation of the mucous membranes - and of the respiratory organs, in particular - and cause hypersensitive reactions. There is a risk of hypersensitization if the vapour or spray mist is inhaled. When using materials containing isocyanates, all precautions relating to the handling of solvents should be carefully followed. In particular, care should be taken not to inhale spray mist or vapour. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.