


Always use correct Personal Protective Equipment

## AquaLAQ COLOUR COAT

### Description




AquaLAQ Colour Coat is a single pack waterborne acrylic, using the latest waterborne technology. Whilst easy to use and fast drying, AquaLAQ dries to an extremely durable finish and has been designed specifically for kitchens, shop fittings and other types of furniture finishing. The rheology of AquaLAQ allows this product to be very user friendly by minimising applicator error. AquaLAQ is very easy to touch up when necessary with excellent sandability. Colour choice is any Resene colour. Colour comes in standard satin finish & other gloss levels available with application of clear top coat.

### Key benefits



- Excellent UV resistance
- No solvents and no explosion/fire risk
- Low to no odour
- Low VOC
- Extremely fast drying
- Applied with standard industry spray equipment
- One to two coat coverage for most colours

### Products



PRODUCT "READY FOR USE" RFU

### Properties




<b>Product Type:</b>	Waterborne Acrylic
<b>Colour:</b>	Any Resene colour
<b>Pot Life:</b>	N/A – 2 years shelf life
<b>Induction Time:</b>	N/A
<b>Application equipment:</b>	Pressure pot, suction, gravity or Airless.
<b>Recommended DFT:</b>	30um
<b>Recommended WFT:</b>	100um
<b>Theoretical Coverage:</b>	8 to 10 sqm per Litre
<b>Volume Solids:</b>	25.3%
<b>Recoat-ability:</b>	Approximately 1hour, subject to ideal application conditions (Info available from Resene tech rep)
<b>VOC:</b>	Under 60 grms per litre
<b>Durability:</b>	Extremely good
<b>UV resistance:</b>	Excellent
<b>Gloss Level:</b>	Available in varied gloss levels
<b>Levelling:</b>	Excellent
<b>Vertical Holdup:</b>	Excellent

No warranty either expressed or implied is made by RALI in this document, which is a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product or its properties shall conform to that description, nor is the description of the product and its properties a warranty by RALI that the goods are suitable for a particular purpose. Do not apply paint if relative humidity is above 85% or temperature is within 3 deg C of Dew Point being the MPT or Minimum Paint Temperature.

### Always use correct Personal Protective Equipment

#### Substrates



Can be applied over correctly prepared:

- MDF board
- Wood substrates

#### Surface Preparation



**Wood substrates:** All wood substrates should be sanded and primed/sealed With AquaLAQ quick dry sealer, or AquaLAQ NGR Primer Sealer. Very low odour/low solvent content.

#### Spray Equipment:



##### Airless Spray Gun

**Tip Size:** Graco FFLP 512-513

**Spray Pressure:** 2000-3000 PSI



##### Air Assisted Airless

**Tip Size:** 10 – 13 Thou

**Spray Pressure:** 2 Bar



##### Conventional Spray

**Tip Size:** 1.4-1.8

**Spray Pressure:** 2 Bar

#### Note:

- 1) When spraying, use the correct gun set up as recommended by your equipment supplier.
- 2) Application techniques should be adjusted as necessary to achieve the recommended dry film thickness. It is good practice to check this process on a small sample prior taking on a large project.
- 3) If you do not have a controlled environment with good air flow to spray in, it is good practice NOT to continue if relative humidity is above 65% and in particular if temperatures are below 10°C or below 3°C of Dew Point.
- 4) All spray setups are recommended starting points and may need adjustments to suit the equipment and conditions.

#### Directions For Use



##### Mixing:

Stir thoroughly, mixing from the bottom of the pail towards the top.

##### Thinning:

Thinning should not normally be required and should only be done, after consultation with the supplier tech rep

##### Application Method:

Standard procedure but consultation with supplier tech rep is advisable.

##### Dry Time:

Touch dry in 10 to 15 minutes subject to ideal applicator conditions. Minimum 10degrees, up to 65% humidity with good airflow.

No warranty either expressed or implied is made by RALI in this document, which is a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product or its properties shall conform to that description, nor is the description of the product and its properties a warranty by RALI that the goods are suitable for a particular purpose. Do not apply paint if relative humidity is above 85% or temperature is within 3 deg C of Dew Point being the MPT or Minimum Paint Temperature.

**Always use correct Personal Protective Equipment**

**No. of Coats:** 1 to 2 coats.

### Drying and curing of waterborne coatings:

- 1) *Ensure air temperature is at least 10deg C and rising at time of application*
- 2) *Ensure humidity is less than 65% rH and falling*
- 3) *Ensure no precipitation is forecast if outside for 4 hours after completion of application*
- 4) *Ideal environmental conditions are 15-25deg C with a breeze of approximately 15km/h, and rH of less than 65%.*
- 5) *Direct hot sunlight can cause skinning of the painted surface, so protect if possible in these conditions.*

### Health & Safety



ALWAYS READ THE SAFETY DATY SHEET (SDS) PRIOR TO USE.  
Observe the precautionary notices displayed on the container.

### Transport & Storage



**Sizes:** 1L, 4L, 10L

**Dangerous Goods: UN:** N/A

**Hazchem:** N/A

**Packing Group:** N/A

**Shipment name:** PAINT

**Flash point:** N/A

No warranty either expressed or implied is made by RALI in this document, which is a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product or its properties shall conform to that description, nor is the description of the product and its properties a warranty by RALI that the goods are suitable for a particular purpose. Do not apply paint if relative humidity is above 85% or temperature is within 3 deg C of Dew Point being the MPT or Minimum Paint Temperature.